



TECHNICAL INFORMATION

PARQUET VARNISH



DESCRIPTION:

Single-component polyurethane varnish for wooden floors with high hardness and chemical resistance. Resistant to detergents, alcohol and abrasion.

Features:

-) Excellent leveling and brushability.
-) Scratch-resistant.
-) Chemical resistant.
-) Fast drying.
-) High weatherproof and ultraviolet radiation. With UV filter.
-) High hardness and elasticity.
-) Compatible with underfloor heating.

TECHNICAL DATA:

Fixed vehicle	Urethane modified synthetic resins.	
Colour	According to VARNISH - LASUR colour chart.	
Gloss	Gloss. 20°: > 75 GU	UNE-EN ISO 2813
Solids by weight	52 %	UNE-EN ISO 3251
Solids by volume	48 %	UNE 48090
Viscosity	45 – 55 KU (23 ± 2 °C)	UNE 48076
Specific weight	0.85 – 0.95 kg/l (23 ± 2 °C)	UNE-EN ISO 2811-1
Theoretical spreading rate	10 – 14 m ² /l and coat. Take in mind application leaking, surface irregularities, etc.	
Total drying	4 – 6 hours.	UNE 48301
Repaint	12 – 24 hours.	
Solvent	Aliphatic hydrocarbons.	

EU limit value for this product (cat. A/e): 400 g/l (2010). Max. content VOC: 400 g/l

APPLICATION:

Suitable for the decoration and protection of wooden surfaces, both indoors and outdoors, such as parquet floors, wooden stairs, floors, doors, windows, chairs, tables, etc.

INSTRUCTIONS FOR USE:

Application methods: brush, roller or spray.

Thinner and cleaning utensils: SYNTETIC AND GREASE SOLVENT.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14


E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

PARQUET VARNISH



Painted surfaces must be dry and clean of dust, rust, grease, etc. and without drafts.

Remove peeling and non-adhering varnish by stripping, scraping or sanding. It is necessary to eliminate waxes and cleaning products that could affect the adhesion of the product.

Bare wood can be stained with PRIMER PROTECTION OF THE WOOD according to VARNISH AND LASUR CHART.

On varnished floors or floating floors, it is appropriate to lightly sand (120 grit) to generate proper adhesion.

Apply with a brush or roller in the direction of the wood grain.

The floor can be walked on after 24 hours, but care must be taken for 10 days, which is the period that the product needs to acquire maximum hardness.

In general, we recommend:

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply in full sun or high temperatures of the surface.
-) Perfectly mix the product before use.

PRESENTATION:

Metallic packaging of: 0.250 L; 0.750 L; 4 L

STORAGE:

24 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>