



TECHNICAL INFORMATION

DECO-ESTUC

DESCRIPTION:

Decorative revetment /coating for obtaining marble imitative effects.

Features:

-) Easy application.
-) Excellent leveling.
-) Excellent adhesion to the surf.
-) Touch cold and smooth.

TECHNICAL DATA:

Fixed vehicle	Copolymer acrylic.	
Colour	According to DECO-ESTUC colour chart.	
Solids by weight	72 %	UNE-EN ISO 3251
Solids by volume	47 %	UNE 48090
Specific weight	1.55 – 1.65 Kg./l (23 ± 2 °C)	UNE-EN ISO 2811-1
pH	8.0 – 10.0 (23 ± 2 °C)	UNE-EN ISO 787-9
Theoretical spreading rate	1 – 2 m ² /Kg. (0.5 – 1 Kg./m ²). Take in mind application leaking, surface irregularities, etc.	
Total drying	2 hours.	UNE 48301
Repaint	24 hours.	
Solvent	Water.	
Reaction to fire	Class M-1	UNE 23727
Reaction to fire	Bs1d0	UNE-EN 13501-1:2007

EU limit value for this product (cat. A/I): 200 g/l (2010). Max. content VOC: 10 g/l

APPLICATION:

Decorative coating designed to get different marble appearance effects, with a cold and smooth touch. The best choice to get elegant finishes of classic Venetian designs.

INSTRUCTIONS FOR USE:

Application methods: stainless steel trowel or spatula.

Thinner and cleaning of tools: Water.

1. Substrate preparation

It can be used over any kind of support, painted surfaces, plaster, plasterboard walls, walls with plaster or cement plaster, etc.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

DECO-ESTUC

Surfaces should be dry and free of dust, rust, grease, etc. and primed properly with SELLADORA, SELLADORA AQUA, DECOKRILL PENETRANTE, or DECOKRIL. It also can be given as a priming layer one coat of DECORTEX applied with roll.

In areas with poor adherence (powdery walls, surfaces with little pore, etc.) Should be applied initially DECOKRIL PENETRANTE to increase the adherence.

It is generally recommended:

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply elevated temperatures support.
-) Perfectly homogenize the product before use.

2. Product preparation

Do not dilute. The product is ready to use.

Perfectly homogenize the product before use.

If it is desired colouring may be used UNIVERSAL DYE DECOLOR, at most 5%. First of all shake well DECO-ESTUC and then add the dye and stir until a complete homogenization.

3. Application

Spread with a stainless steel trowel uniformly and compacted to make the surface smooth and uniform. After 24 hours, lightly sand and apply a second layer with a stainless steel trowel leaving the surface smooth and uniform. After 24 hours proceed with a spatula to spatula the surface with DECO-ESTUC obtained different effects of imitative marble finishing by the superimposing of the coats. Then you can proceed to rub or polish the surface with fine sandpaper 1000-2000 or stainless steel trowel to obtain the desired brightness. You can increase the brightness if we friction with spatula.

4. Finishing

After 48 hours protect the stucco by applying a protective wax special for protective wax stucco.

If the product is applied outdoors we protect from moisture with two coats of VARNISH REPELLENT WATER DECOLOR.

PRESENTATION:

Plastic packaging of: 5 Kg.; 15 Kg.

STORAGE:

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5

Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

DECO-ESTUC

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>