TECHNICAL INFORMATION

DECO-UNION



DESCRIPTION:

DECO-UNION is an adherence under-coat primer for mortar of concrete and plaster with a long-time open application. Excellent penetration into supports allowing to work on it after 24 hours of application. Avoid the fast elimination of water from the mortars permitting a correct curing of the same and assuring a good adherence among coats.

Features:

- Excellent adherence over most common brickwork materials.
- Ready for use.
- Eco friendly.

TECHNICAL DATA:

Fixed vehicle	Resins special acrylic.	
Colour	White.	
Gloss	Matt.	
Solids by weight	40 %	UNE-EN ISO 3251
Solids by volume	38 %	UNE 48090
Specific weight	0.95 – 1.05 Kg./l (23 ± 2 ºC)	UNE-EN ISO 2811-1
pH	7.0 – 8.0 (23 ± 2 ºC)	UNE-EN ISO 787-9
Theoretical spreading rate	0.150 – 0.200 Kg./m^2. Take in mind application leaking, surface irregularities, etc.	
Solvent	Water.	
Reaction to fire	Class M-1	UNE 23727
Reaction to fire	Bs1d0	UNE-EN 13501-1:2007

EU limit value for this product (cat. A/h): 30 g/l (2010). Max. content VOC: 0 g/l

APLICATION:

Adherence undercoat primer for concrete and plaster mortars, with a long time open application after 24 hours after application. After application you can make perfect and secure unions with different coats of plaster, concrete, etc. It is perfect for join new with old mortar works, also can be used in new flooring works, re-flooring, brickworks over pillars, mortar works, etc.

INSTRUCTIONS FOR USE:

Application methods: brush, roller or spray.
Thinner and cleaning utensils: Water.

Pinturas Decolor
Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain
Phone: +34 967 44 17 14 Fax: +34 967 44 33 54
E-mail: dptotecnico@decolor.com http://www.decolor.com

TECHNICAL INFORMATION

DECO-UNION



Surfaces must be consolidated, dry and clean of dust, oxide, grease, and free of rest of formwork products.

Apply coats until get a performance of 0.150-0.200 kg/m^2 non diluted.

After 45 minutes of the application you can apply over the primed surfaces mortar or plaster until 48 hours passed.

Over non porous surfaces (some metals, plastics, very polished cements, etc.) should be applied primer.

In general we recommend:

- Apply between 5 ºC and 35 ºC.
- Mix thoroughly before utilization.
- Not advisable to apply on surfaces with high temperature.
- Not advisable to apply on surfaces with permanent humidity.
- Avoid to stain with dust since may loss adherence.

PRESENTATION:

Plastic packaging of: 1 L; 5 L; 20 L

STORAGE:

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor
Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain
Phone: +34 967 44 17 14 Fax: +34 967 44 33 54
E-mail: dptotecnico@decolor.com http://www.decolor.com