



TECHNICAL INFORMATION

MULTISURFACES HIGH ADHESION PRIMER



DESCRIPTION:

Multi-purpose primer waterborne for interior and exteriors, it makes easier the adherence for following paint coats on glass, tiles, ceramic, PVC, wood, galvanized steel, aluminium, some plastic, etc.

Features:

-) Excellent adherence on critical surfaces (glass, tiles, ceramic, PVC, wood, galvanized steel, aluminium, some plastic, etc.)
-) Knot Insulation and tannin locking on wood and tropical wood.
-) Resistant to water, and weather. No yellowish.
-) Excellent levelling and brushability.
-) Great hardness and resistant to scratches.
-) Single component.
-) Fast drying.
-) Interior and exterior
-) Eco friendly.

TECHNICAL DATA:

Fixed vehicle	Acrylic resin.	
Colour	White.	
Gloss	Matt.	UNE-EN ISO 2813
Solids by weight	47 %	UNE-EN ISO 3251
Solids by volume	31 %	UNE 48090
Viscosity	85 – 95 KU (23 ± 2 °C)	UNE 48076
Specific weight	1.15 – 1.25 Kg./l (23 ± 2 °C)	UNE-EN ISO 2811-1
pH	< 6.0 (23 ± 2 °C)	UNE-EN ISO 787-9
Theoretical spreading rate	12 – 16 m ² /l and coat. Take in mind application leaking, surface irregularities, etc.	
Recommended thickness	60 – 80 microns wet; 19 – 25 microns dry per coat. Apply 2 coats as finish.	
Total drying	30 – 60 minutes.	UNE 48301
Repaint	6 – 8 hours.	
Solvent	Water.	
Reaction to fire	Class M-1	UNE 23727
Reaction to fire	Bs1d0	UNE-EN 13501-1:2007

EU limit value for this product (cat. A/i): 140 g/l (2010). Max. content VOC: 40 g/l

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

MULTISURFACES HIGH ADHESION PRIMER



Adhesion / Lattice cut test UNE-EN ISO 2409		
Surface	Details	Resulted
Tiles	50 µm dry applied directly; 7 days at room temperature	0/0/0
Galvanised steel	50 µm dry applied directly; 7 days at room temperature	0/0/0
Aluminium	50 µm dry applied directly; 7 days at room temperature	0/0/0
PVC	50 µm dry applied directly; 7 days at room temperature	0/0/0

APPLICATION:

Multi-purpose waterborne primer it makes easier the adherence for following paint coats on critical surfaces such as glass, tiles, ceramic, wood, galvanized steel, aluminium, some plastic, etc. for interior and exterior.

INSTRUCTIONS FOR USE:

Application methods: brush, roller or spray.

Cleaning utensils: Water.

Painted surfaces must be dry and clean of dust, rust, grease, etc.

Product ready for use.

) Unpainted surfaces:

- PVC and plastic: Sand before applying to facilitate the adherence. After that apply two coats without dilution. It is advisable to make a test over the plastic to check the adherence.
- Glass, tile, ceramic, etc.: Apply two or three coats without dilution. It is advisable to make a test over surfaces non porous.
- Wood: Apply two or three coats without dilution.
- Galvanized steel, aluminium: Apply two or three coats without dilution.
- Cement and concrete: First concrete must be cured for which one month must have elapsed since its application. Treat the surface with hydrochloric (hydrochloric acid) diluted 10-15% with water to neutralize the alkalinity of cement, then rinse and let dry. Apply two coats without dilution.

) Painted surfaces:

- If the paint is in poor condition, remove completely and proceed as in unpainted surfaces.
- If the paint is in good condition, sand and apply MULTISURFACES HIGH ADHESION PRIMER.

If you want to colour it can be used DECOLOR WATER COLORANT or DECOLOR UNIVERSAL COLORANT, at most 5%.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

MULTISURFACES HIGH ADHESION PRIMER



In general, we recommend:

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply in full sun or high temperatures of the surface.
-) Perfectly mix the product before use.

PRESENTATION:

Metal packaging of: 750 ml; 4 L

STORAGE:

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>