



TECHNICAL INFORMATION

ANTI-HUMIDITY AQUA PRIMER



DESCRIPTION:

Waterproofing primer water based for humidity and efflorescence.

Features:

-) Avoid passing of humidity.
-) Excellent adherence over construction materials.
-) Very good resistance to alkalis.
-) Excellent washability.
-) Excellent leveling and brushability.
-) Fast drying.
-) Odourless and eco friendly.

TECHNICAL DATA:

Fixed vehicle	Resins specials.	
Colour	White.	
Gloss	Matt.	
Solids by weight	75 %	UNE-EN ISO 3251
Solids by volume	62 %	UNE 48090
Viscosity	112 – 118 KU (23 ± 2 °C)	UNE 48076
Specific weight	1.35 – 1.45 Kg./l (23 ± 2 °C)	UNE-EN ISO 2811-1
pH	8.0 – 10.0 (23 ± 2 °C)	UNE-EN ISO 787-9
Theoretical spreading rate	6 – 8 m ² /l. and coat. Take in mind application leaking, surface irregularities, etc.	
Recommended thickness	125 – 175 microns wet; 75 – 110 microns dry per coat. Apply 2 coats as finish.	
Total drying	30 – 60 minutes.	UNE 48301
Repaint	6 – 8 hours.	
Solvent	Water.	
Reaction to fire	Class M-1	UNE 23727
Reaction to fire	Bs1d0	UNE-EN 13501-1:2007
Elongation at break	130%	UNE 53413
Tensile strength	1.50 MPa (15 Kg./cm ²)	UNE 53413
Permeability to water vapour	Class III (Low)	UNE-EN ISO 7783-2
Water absorption	4% approximately	at 48 hours

EU limit value for this product (cat. A/g): 30 g/l (2010). Max. content VOC: 0.5 g/l

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

ANTI-HUMIDITY AQUA PRIMER



APPLICATION:

Waterproofing product indicated for humidity and efflorescence, making a barrier and stopping the pass of humidity due to water rain, water leaking, etc.

INSTRUCTIONS FOR USE:

Application methods: brush, roller or spray.
Thinner and cleaning utensils: Water.

Painted surfaces must be dry and clean of dust, rust, grease, efflorescence, etc.

) Unpainted surfaces:

- General brickworks: Apply a first coat diluted 5% with water. After 6 hours apply a second coat non diluted or diluted maximum at 5%. Then you can apply a top coat.

) Painted surfaces:

- Most of the case the paint will be in bad conditions: blistering or flake, with saltpetre, mould, etc. In these cases we advise to remove completely the old paint and proceed as non painted surfaces.

In general we recommend:

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply in full sun or high temperatures of the surface.
-) Perfectly mix the product before use.
-) In case of contamination by fungus or algae:
 - Wash with a solution of water and bleach to 10%.
 - Rinse with water.
 - Let dry completely before beginning to paint.
 - Use products with protection against FUNGUS.
-) In case of presence of saline efflorescence:
 - Brush and wash with hydrochloric acid diluted to 10% with water.
 - Rinse with water.
 - Let dry completely before beginning to paint.

PRESENTATION:

Plastic packaging of: 0.750 Litres; 4 Litres

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14 Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

ANTI-HUMIDITY AQUA PRIMER



STORAGE:

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain
Phone: +34 967 44 17 14 Fax: +34 967 44 33 54
E-mail: dptotecnico@decolor.com <http://www.decolor.com>