



TECHNICAL INFORMATION

FLOOR PRIMER



DESCRIPTION:

Primer solvent borne for interior and exteriors, it makes easier the adherence for following paint coats on cement, concrete, terrazzo, etc.

Features:

-) Excellent adherence on surface cement, concrete, terrazzo, etc.
-) Equalizes the absorption of the support and maximizes the adherence.
-) Resistant to water, and weather. No yellowish.
-) Single component.
-) Fast drying.
-) Interior and exterior.

TECHNICAL DATA:

Fixed vehicle	Acrylic resin-silane.	
Colour	Colourless.	
Specific weight	0.85 – 0.95 Kg./l (23 ± 2 °C)	UNE-EN ISO 2811-1
Theoretical spreading rate	10 – 12 m ² /l. Take in mind application leaking, surface irregularities, etc.	
Total drying	30 – 60 minutes.	UNE 48301
Repaint	12 – 24 hours.	
Traction adherence	> 6 N/mm ² (cement board/7 days at 23 °C/100 ↑m dry)	UNE-EN ISO 4824
Solvent	Aromatic solvent.	

EU limit value for this product (cat. A/h): 750 g/l (2010). Max. content VOC: 750 g/l

APPLICATION:

Solvent borne primer it makes easier the adherence for following paint coats on cement, concrete, terrazzo, etc. for interior and exterior.

As primer and sealing supports concrete or cement, prior to application of coatings of floors.

INSTRUCTIONS FOR USE:

Application methods: brush, roller or spray.

Thinner and cleaning utensils: ACRYLIC SOLVENT.

Painted surfaces must be dry and clean of dust, rust, grease, etc.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14 Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

FLOOR PRIMER



- Cement, concrete: The concrete must first be set for which it must have been 1 month since its application.

The weak parts of the concrete must be eliminated and all possible defects of the support must be repaired.

The surface must have a suitable roughness, recommending its preparation by means of a sander with a diamond stone or shot blasting machine.

Low or medium porosity concrete: 1 layer of FLOOR PRIMER.
High porosity concrete: 2 layers of FLOOR PRIMER.

In general, we recommend:

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply in full sun or high temperatures of the surface.
-) Perfectly mix the product before use.

PRESENTATION:

Metallic packaging of: 4 Litres; 15 Litres

STORAGE:

24 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14 Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>