



TECHNICAL INFORMATION

WOOD STAIN – LASURE



DESCRIPTION:

Wood stain/Lasur protector of high quality wood from synthetic resins and UV solar filter, for the protection and decoration of wood exposed to the weather.

Features:

-) Highlight the natural appearing of the wood.
-) Contains UV solar filter.
-) No peeling off.
-) Micro porous film.
-) Breathable to water vapour (inside the wood).
-) No cracking or flaking.
-) Fast drying.
-) Interior and exterior.

TECHNICAL DATA:

Fixed vehicle	Synthetics resins.	
Colour	Chart colours BARNIZ – LASUR.	
Gloss	Satin.	
Solids by weight	32 %	UNE-EN ISO 3251
Solids by volume	29 %	UNE 48090
Viscosity	35 – 45 KU (23 ± 2 °C)	UNE 48076
Specific weight	0.80 – 0.90 Kg./l (23 ± 2 °C)	UNE-EN ISO 2811-1
Theoretical spreading rate	12 – 14 m ² /l and coat. Take in mind application leaking, surface irregularities, etc.	
Recommended thickness	70 – 80 microns wet; 20 – 23 microns dry per coat. Apply 2 coats as finish.	
Total drying	4 – 6 hours at 23 °C and 55% relative humidity. Depend on air temperature and ventilation.	UNE 48301
Repaint	12 – 24 hours.	
Solvent	Aliphatic hydrocarbons.	

EU limit value for this product (cat. A/f): 700 g/l (2010). Max. content VOC: 500 g/l

APLICACION:

Decoration and protection of wood exposed to the weather. Penetrates wood, highlighting its natural veining.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14 Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

WOOD STAIN – LASURE



INSTRUCTIONS FOR USE:

Application methods: brush or spray.

Thinner and cleaning utensils: ODOURLESS SOLVENT.

Painted surfaces must be dry and clean of dust, rust, grease, etc.

The number of coats to apply of tinted WOOD STAIN - LASURE will affect the obtained final colour.

The wood highly resinous must be cleaned previously with SYNTHETIC AND GREASE SOLVENT, UNIVERSAL SOLVENT or ODOURLESS SOLVENT, to avoid problems during the drying.

) Unpainted surfaces:

- Standard wood: Apply the product diluted 5% with ODOURLESS SOLVENT, to obtain a perfect finishing is recommended to apply 3 coats waiting and sanding between application around 24 hours.

) Painted surfaces:

- Remove paint and varnish by polishing or sanding until complete elimination. After that proceed as non painted surfaces

If you want to colour it can be used DECOLOR UNIVERSAL COLORANT, at most 5%.

In general we recommend:

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply in full sun or high temperatures of the surface.
-) Perfectly mix the product before use.

PRESENTATION:

Plastic packaging of: 0.250 Litres; 0.750 Litres; 4 Litres

STORAGE:

24 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.