



TECHNICAL INFORMATION

SEALING



DESCRIPTION:

High quality sealer primer for the preparation of surfaces of wood and plaster.

Features:

-) Improve the adherence fixing the dusty substrates.
-) Uniform sealing making better the quality of the finish.
-) Fast drying.
-) Easy sanding.
-) Exterior and interior.

TECHNICAL DATA

Fixed vehicle	Resins alkyds.	
Colour	White.	
Gloss	Matt.	UNE-EN ISO 2813
Solids by weight	81 %	UNE-EN ISO 3251
Solids by volume	65 %	UNE 48090
Viscosity	85 – 95 KU (23 ± 2 °C)	UNE 48076
Specific weight	1.50 – 1.60 Kg./l (23 ± 2 °C)	UNE-EN ISO 2811-1
Theoretical spreading rate	10 – 14 m ² /l and coat. Take in mind application leaking, surface irregularities, etc.	
Recommended thickness	70 – 100 microns wet; 45 – 65 microns dry per coat. Apply 2 coats as finish.	
Total drying	2 – 3 hours.	UNE 48301
Repaint	24 hours.	
Solvent	Aliphatic hydrocarbons.	
Reaction to fire	Class M-1	UNE 23727
Reaction to fire	Bs1d0	UNE-EN 13501-1:2007

EU limit value for this product (cat. A/g): 350 g/l (2010). Max. content VOC: 290 g/l

APPLICATION:

Preparation and sealing of surfaces of wood, plastered walls and ceilings, etc. both indoors and outdoors.

INSTRUCTIONS FOR USE:

Application methods: brush, roller or spray.

Thinner and cleaning utensils: SYNTHETIC AND FATTY SOLVENT.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14 Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

SEALING



Painted surfaces must be dry and clean of dust, rust, grease, etc.

) Unpainted surfaces:

- Wood: Sand the surface before applying the SEALING. Apply the SEALING on the surface to be treated and sand before applying the finishing product.
- Plaster: Dilute the SEALING between 5 – 10% to improve the sealing in depth.

If you want to colour it can be used DECOLOR UNIVERSAL COLORANT, at most 5%.

In general we recommend:

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply in full sun or high temperatures of the surface.
-) Perfectly mix the product before use.

PRESENTATION:

Metallic packaging of: 0.750 Litres; 4 Litres

STORAGE:

24 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14 Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>