



TECHNICAL INFORMATION

ALBOR ACRYLIC AQUA



DESCRIPTION:

High quality lacquer enamel water based formulated from acrylics resins. Decoration and protection of surfaces as doors, windows, walls, railings, furniture, etc.

Features:

-) High covering.
-) No yellowing.
-) Excellent leveling and resistant to scratches and hits.
-) Resistant to chemical products.
-) Exterior weather resistant.
-) Odourless and eco friendly.

TECHNICAL DATA:

Fixed vehicle	Acrylic resin.	
Colour	White.	
Gloss	Matt. 85°: <10 GU	UNE-EN ISO 2813
Solids by weight	62 %	UNE-EN ISO 3251
Solids by volume	44 %	UNE 48090
Viscosity	95 – 105 KU (23 ± 2 °C)	UNE 48076
Specific weight	1.30 – 1.40 Kg./l (23 ± 2 °C)	UNE-EN ISO 2811-1
pH	8.0 – 10.0 (23 ± 2 °C)	UNE-EN ISO 787-9
Theoretical spreading rate	12 – 14 m ² /l and coat. Take in mind application leaking, surface irregularities, etc.	
Recommended thickness	70 – 85 microns wet; 31 – 38 microns dry per coat. Apply 2 coats as finish.	
Total drying	1 hour.	UNE 48301
Repaint	6 – 8 hours.	
Solvent	Water.	
Wet scrub resistance	Class 1	UNE-EN 13300
Reaction to fire	Class M-1	UNE 23727
Reaction to fire	Bs1d0	UNE-EN 13501-1:2007

EU limit value for this product (cat. A/d): 130 g/l (2010). Max. content VOC: 35 g/l

APPLICATION:

Decoration and protection of surfaces of iron/steel, wood, plaster, cement, etc. both in interior surfaces and exterior. For example: doors, windows, walls, railings, furniture, etc.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5
 Apdo. 106 – 02630 La Roda (Albacete) Spain
 Phone: +34 967 44 17 14 Fax: +34 967 44 33 54
 E-mail: dptotecnico@decolor.com <http://www.decolor.com>



TECHNICAL INFORMATION

ALBOR ACRYLIC AQUA



INSTRUCTIONS FOR USE:

Application methods: brush, roller or spray.

Thinner and cleaning utensils: Water.

Painted surfaces must be dry and clean of dust, rust, grease, etc. and primed properly.

) Unpainted surfaces:

- Iron, steel: Prime with PRIMER POLYVALENT AQUA. Apply two coats of ALBOR ACRYLIC AQUA for finish.
- Gypsum, cement, wood: Prime with SEALER AQUA. Apply two coats of ALBOR ACRYLIC AQUA for finish.

) Painted surfaces:

- If the paint is in poor condition, remove completely and proceed as in unpainted surfaces.
- If the paint is in good condition, sand and apply two coats of ALBOR ACRYLIC AQUA.

If you want to colour it can be used DECOLOR WATER COLORANT or DECOLOR UNIVERSAL COLORANT, at most 5%.

In general we recommend:

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply in full sun or high temperatures of the surface.
-) Perfectly mix the product before use.

PRESENTATION:

Plastic packaging of: 0.750 Litres; 4 Litres; 15 Litres

STORAGE:

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5

Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>