TECHNICAL INFORMATION

ALBOR MATT ANTI-RUST



DESCRIPTION:

High quality matt anti-rust synthetic enamel made out from alkyd resins with polyurethane and containing inhibitor of rusting.

Features:

- High covering.
- Stable to yellowish.
- Excellent leveling and resistant to scratches and hits.
- Resistant to chemical products.
- Waterproofing, anti-rust and exterior resistant.
- Lead free.

TECHNICAL DATA:

Fixed vehicle	Alkyd with polyurethane resins.	
Colour	According to ALBOR colour chart.	
Gloss	Matt. 85º: < 10 GU	UNE-EN ISO 2813
Solids by weight	81 % White 72 % Black	UNE-EN ISO 3251
Solids by volume	63 % White 55 % Black	UNE 48090
Viscosity	80 – 90 KU (23 ± 2 ºC)	UNE 48076
Specific weight	1.40 – 1.50 Kg./l (23 ± 2 ºC) White 1.20 – 1.30 Kg./l (23 ± 2 ºC) Black	UNE-EN ISO 2811-1
Theoretical spreading rate	12 – 16 m^2/l and coat. Take in mind application leaking, surface irregularities, etc.	
Recommended thickness	60 – 80 microns wet; 35 – 45 microns dry per coat. Apply 2 coats as finish.	
Total drying	4 – 5 hours.	UNE 48301
Repaint	12 – 24 hours.	
Solvent	Aliphatic solvent.	
Reaction to fire	Class M-1	UNE 23727
Reaction to fire	Bs1d0	UNE-EN 13501-1:2007

EU limit value for this product (cat. A/d): 300 g/l (2010). Max. content VOC: 300 g/l

APLICATION:

Decoration and protection of surfaces of iron/steel, wood, plaster, machinery, etc. both in interior surfaces and exterior where you want to obtain a matt finishing.

Pinturas Decolor
Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain
Phone: +34 967 44 17 14 Fax: +34 967 44 33 54
E-mail: dptotecnico@decolor.com http://www.decolor.com

TECHNICAL INFORMATION

ALBOR MATT ANTI-RUST



INSTRUCTIONS FOR USE:

Application methods: brush, roller or spray.
Thinner and cleaning utensils: SOLVENT SYNTHETIC AND FATTY.

Painted surfaces must be dry and clean of dust, rust, grease, etc. and primed properly.

- Unpainted surfaces:

  - Iron, steel: Apply directly ALBOR MATT ANTI-RUST in atmospheres of low or moderate aggression. It is advisable to prime with ANTI-RUST PRIMER DECOLOR or POLYVALENT PRIMER for better anticorrosive power.
  - Gypsum, cement, wood: Prime with SEALER DECOLOR. Apply two coats of ALBOR MATT ANTI-RUST for finish.

- Painted surfaces:

  - If the paint is in poor condition, remove completely and proceed as in unpainted surfaces.
  - If the paint is in good condition, sand and apply two coats of ALBOR MATT ANTI-RUST.

If you want to colour it can be used DECOLOR UNIVERSAL COLORANT, at most 5%.

In general we recommend:

- Apply between 5 °C and 35 °C.
- It is not recommended to apply in full sun or high temperatures of the surface.
- Perfectly mix the product before use.

PRESENTATION:

Metal packaging of: 0.250 Litres; 0.750 Litres; 4 Litres

STORAGE:

24 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor
Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain
Phone: +34 967 44 17 14 Fax: +34 967 44 33 54
E-mail: dptotecnico@decolor.com http://www.decolor.com