



TECHNICAL INFORMATION

ALKIL POLIMUL 202



DESCRIPTION:

Water based concentrate primer, high fixing and penetrating power over deteriorated surfaces, improving the adherence and making uniform the absorption.

Features:

-) Excellent adherence over surfaces.
-) Make uniform the absorption.
-) Water and weather resistant.
-) Exterior and Interior.

TECHNICAL DATA:

Fixed vehicle	Vinyl acetate homopolymer.	
Colour	Colourless.	
Solids by weight	55 %	UNE-EN ISO 3251
Solids by volume	55 %	UNE 48090
Specific weight	1.00 – 1.10 Kg./l (23 ± 2 °C)	UNE-EN ISO 2811-1
pH	6.0 – 7.0 (23 ± 2 °C)	UNE-EN ISO 787-9
Theoretical spreading rate	25 – 33 m ² /l and coat. Take in mind application leaking, surface irregularities, etc.	
Total drying	30 – 60 minutes.	UNE 48301
Repaint	4 hours.	
Solvent	Water.	

EU limit value for this product (cat. A/h): 30 g/l (2010). Max. content VOC: 5 g/l

APPLICATION:

Primer to be applied over walls and ceilings, old paints, interior and exterior, and finish with a plastic paint.

INSTRUCTIONS FOR USE:

Application methods: brush, roller or spray.

Thinner and cleaning utensils: Water.

Dilute 1 part of ALKIL POLIMUL 202 with 4 or 5 parts of water.

Painted surfaces must be dry and clean of dust, rust, grease, etc.

-) Unpainted surfaces:

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

ALKIL POLIMUL 202



- Dead or powdery plaster, cement or concrete: Fix the surfaces to be painted with a dilution of 1 part of ALKIL POLIMUL 202 and 4/5 parts of water. Once is dry apply the plastic paint as a top coat.

) Painted surfaces:

- If the paint is in poor condition, remove completely and proceed as in unpainted surfaces.
- If the paint is in good conditions, wash, sand and fix the surface with a dilution of 1 part of ALKIL POLIMUL 202 and 4/5 parts of water. Once is dry apply the plastic paint as a top coat.

In general we recommend:

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply in full sun or high temperatures of the surface.
-) Perfectly mix the product before use.

PRESENTATION:

Plastic packaging of: 1 Litres; 5 Litres; 20 Litres

STORAGE:

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14 Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>