



TECHNICAL INFORMATION

VARNISH AMBAR AQUA



DESCRIPTION:

High quality varnish water based formulated from acrylics resins. Extraordinary hardness, applicable on floors, furniture, etc. With UV filter.

Features:

-) Does not modify the natural grain of the wood.
-) Excellent leveling and brushability.
-) Scratch and impact resistant.
-) Resistant to cleaning products.
-) Fast drying.
-) High hardness and elasticity.
-) Odourless and eco friendly.

TECHNICAL DATA:

Fixed vehicle	Acrylics resins.	
Colour	According to VARNISH – LASUR.	
Gloss	Gloss. 60°: > 80 GU Satin. 60°: 35 – 45 GU Matt. 60°: < 8 GU	UNE-EN ISO 2813
Solids by weight	37 % Gloss 36 % Satin 40 % Matt	UNE-EN ISO 3251
Solids by volume	34 % Gloss 32 % Satin 35 % Matt	UNE 48090
Viscosity	75 – 85 KU (23 ± 2 °C)	UNE 48076
Specific weight	0.95 – 1.05 kg/l (23 ± 2 °C)	UNE-EN ISO 2811-1
pH	8.0 – 10.0 (23 ± 2 °C)	UNE-EN ISO 787-9
Theoretical spreading rate	12 – 16 m ² /l and coat. Take in mind application leaking, surface irregularities, etc.	
Recommended thickness	60 – 80 microns wet; 20 – 26 microns dry per coat. Apply 2 coats as finish.	
Total drying	30 – 60 minutes.	UNE 48301
Repaint	3 hours.	
Solvent	Water.	
Taber abrasion resistance	< 30 mg (CS-17 – 1kg - 1000 cycles)	UNE-EN ISO 7784-2
Reaction to fire	Class M-1	UNE 23727
Reaction to fire	Bs1d0	UNE-EN 13501-1:2007
Emissions in the indoor air	Class A+	French Legislation Decree No. 2011-321 of March 23, 2011

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

VARNISH AMBAR AQUA



EU limit value for this product (cat. A/e): 130 g/l (2010). Max. content VOC: 40 g/l

APPLICATION:

Decoration and protection of wood surfaces such as floors, furniture, doors, blinds, chairs, tables, etc.

INSTRUCTIONS FOR USE:

Application methods: brush, roller or spray.

Thinner and cleaning utensils: Water.

Painted surfaces must be dry and clean of dust, rust, grease, etc.

) Unpainted surfaces:

- Wood: Apply the first coat diluted 10%. Apply successive layers diluting to 5%. It is convenient to sand between the successive coats for obtaining more adherences.

) Painted surfaces:

- If the varnish is in poor condition, remove completely and proceed as in unpainted surfaces.
- If the varnish is in good condition, sand and apply the varnish.

In general, we recommend:

-) Apply between 5 °C and 35 °C.
-) Perfectly mix the product before use.

PRESENTATION:

Plastic packaging of: 0.750 L; 4 L

STORAGE:

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>