



TECHNICAL INFORMATION

CLIMAT PREMIUM



DESCRIPTION:

Acrylic smooth coating for decoration and protection of all kinds of exterior masonry surfaces. High hydrophobicity in early rain application together with excellent open time in warm climates. Contains film preservative that provides excellent protection against a wide spectrum of fungi and algae.

Characteristics:

-) Excellent hydrophobicity of application in early rain.
-) Excellent open time in warm climates.
-) Resistant to weathering and sunlight.
-) Good flexibility.
-) Fungicide - algaecide.

TECHNICAL DATA:

Fixed vehicle	Acrylic.	
Colour	White and tinting systems DECO-COLOR.	
Gloss	Matt. 60° : 2-3 GU	UNE-EN ISO 2813
Solids by weight	71 %	UNE-EN ISO 3251
Solids by volume	53 %	UNE 48090
Specific weight	1.50 – 1.60 Kg./l (23 ± 2 °C)	UNE-EN ISO 2811-1
pH	>8.5 (23 ± 2 °C)	UNE-EN ISO 787-9
Theoretical spreading rate	8 – 10 m ² /l. Application losses, surface irregularities, etc. must be taken into account.	
Total drying	1 hour.	UNE 48301
Repaint	4 – 6 hours.	
Solvent	Water.	
Reaction to fire	Bs1d0	UNE-EN 13501-1:2007
Wet scrub resistance	Class 1	UNE-EN 13300
Permeability to water vapour	V ₁ (High)	UNE-EN ISO 7783-2
Liquid water transmission rate	W ₃ (Low)	UNE-EN 1062-3
Classification	EN 1062-1 G ₃ E ₂ S ₁ V ₁ W ₃ A ₀ C ₀	UNE-EN 1062-1

EU limit value for this product (cat. A/c): 40 g/l (2010). Max. content VOC: 1 g/l

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14 Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

CLIMAT PREMIUM



APPLICATION:

Smooth acrylic coating for decoration and protection of all kinds of exterior masonry surfaces. High hydrophobicity in early rain applications together with excellent open time in warm climates. Prevents fungal and algae growth and surface tensions. Maintains the appearance of the surface by providing durability, dirt repellency, water repellency, weather resistance, thermal insulation and durable colours with sunlight resistance.

INSTRUCTIONS FOR USE:

Application methods: brush, roller or spray.
Thinner and cleaning utensils: Water.

Painted surfaces must be dry and clean of dust, rust, grease, etc. and primed properly.

If the existing paint is in poor condition, remove it completely.

If the surface shows fungal or algae growth, clean it beforehand.

Brush / Roller: For first coat without primer, or on uneven surfaces, dilute maximum 5% with water.

Spray gun: Dilute maximum 5-10% with water.

In general, we recommend:

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply in full sun or high temperatures of the surface.
-) Perfectly mix the product before use.
-) In case of contamination by fungus or algae:
 - Wash with a solution of water and bleach to 10%.
 - Rinse with water.
 - Let dry completely before beginning to paint.
 - Use products with protection against FUNGUS.
-) In case of presence of saline efflorescence:
 - Brush and wash with hydrochloric acid diluted to 10% with water.
 - Rinse with water.
 - Let dry completely before beginning to paint.

PRESENTATION:

Plastic packaging of: 4 Litres; 14 Litres

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14 Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

CLIMAT PREMIUM



STORAGE:

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14 Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>