



TECHNICAL INFORMATION

DECOKRIL ANCHORAGE



DESCRIPTION:

Granulated fixative prime made with a mixture of selected acrylic and aggregate copolymers, with good fixing, penetration and alkali resistance. It facilitates a perfect anchorage between the RUSTIK-COLOR or the DECO-RUSTIK and certain supports that present difficulty of adhesion (plasters, paints, etc.); while avoiding the different absorptions of the wall.

TECHNICAL DATA:

Colour	Milky white liquid.	
Solids by weight	66%	UNE-EN ISO 3251
Specific weight	1.20 – 1.30 Kg./l (23 ± 2 °C)	UNE-EN ISO 2811-1
pH	8.0 – 10.0 (23 ± 2 °C)	UNE-EN ISO 787-9
Solvent	Water.	

EU limit value for this product (cat. A/h): 30 g/l (2010). Max. content VOC: 0 g/l

APPLICATION:

Fixing on any type of support, painted surfaces, plasters, cement, etc., indoors and outdoors, before applying DECO-RUSTIK or RUSTIK-COLOR or others.

INSTRUCTIONS FOR USE:

Cleaning utensils: Water. Tools and tools will be cleaned with water immediately after use.

Painted surfaces must be dry and clean of dust, rust, grease, etc.

Apply without dilution on the wall to be treated.

In general we recommend:

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply in full sun or high temperatures of the surface.
-) Perfectly mix the product before use.
-) In case of contamination by fungus or algae:
 - Wash with a solution of water and bleach to 10%.
 - Rinse with water.
 - Let dry completely before beginning to paint.
 - Use products with protection against FUNGUS.
-) In case of presence of saline efflorescence:
 - Brush and wash with hydrochloric acid diluted to 10% with water.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
 Apdo. 106 – 02630 La Roda (Albacete) Spain
 Phone: +34 967 44 17 14 Fax: +34 967 44 33 54
 E-mail: dptotecnico@decolor.com <http://www.decolor.com>



TECHNICAL INFORMATION

DECOKRIL ANCHORAGE



- Rinse with water.
- Let dry completely before beginning to paint.

PRESENTATION:

Plastic packaging of: 10 Litres

STORAGE:

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14 Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>