



TECHNICAL INFORMATION

ANTI-HUMIDITY PAINT



DESCRIPTION:

Waterproofing paint for humidity and efflorescence.

Features:

-) Avoid passing of humidity.
-) Excellent adherence over construction materials even if are wet.
-) Very good resistance to alkalis.
-) Resistant to growing of mould.
-) Excellent washability.
-) Excellent leveling and brushability.

TECHNICAL DATA:

Fixed vehicle	Resin polymerized in solvent.	
Colour	White.	
Gloss	Matt.	UNE-EN ISO 2813
Solids by weight	72 %	UNE-EN ISO 3251
Solids by volume	47 %	UNE 48090
Viscosity	90 – 96 KU (23 ± 2 °C)	UNE 48076
Specific weight	1.40 – 1.50 Kg./l (23 ± 2 °C)	UNE-EN ISO 2811-1
Theoretical spreading rate	4 – 6 m ² /l and coat. Take in mind application leaking, surface irregularities, etc.	
Recommended thickness	160 – 250 microns wet; 90 – 135 microns dry per coat. Apply 2 coats as finish.	
Total drying	2 – 3 hours.	UNE 48301
Repaint	24 hours.	
Solvent	Aliphatic hydrocarbons.	
Reaction to fire	Class M-1	UNE 23727
Reaction to fire	Bs1d0	UNE-EN 13501-1:2007

EU limit value for this product (cat. A/g): 350 g/l (2010). Max. content VOC: 350 g/l

APPLICATION:

Waterproofing product indicated for humidity and efflorescence, making a barrier and stopping the pass of humidity due to water rain, water leaking, etc.

INSTRUCTIONS FOR USE:

Application methods: brush, roller or spray.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5
 Apdo. 106 – 02630 La Roda (Albacete) Spain
 Phone: +34 967 44 17 14 Fax: +34 967 44 33 54
 E-mail: dptotecnico@decolor.com <http://www.decolor.com>



TECHNICAL INFORMATION

ANTI-HUMIDITY PAINT



Thinner and cleaning utensils: SYNTHETIC AND FATTY SOLVENT.

Painted surfaces must be dry and clean of dust, rust, grease, efflorescence, etc.

) Unpainted surfaces:

- General brickworks: Apply a first coat diluted 5% with SYNTHETIC AND FATTY SOLVENT. After 24 hours apply a second coat of ANTI-HUMIDITY PAINT non diluted or diluted maximum at 5%. The ANTI-HUMIDITY PAINT is indicated as a white finish, but if desired, any desired product can be applied on it as a finish.

) Painted surfaces:

- Most of the case the paint will be in bad conditions: blistering or flake, with saltpetre, mould, etc. In these cases we advise to remove completely the old paint and proceed as non painted surfaces.

If you want to colour it can be used DECOLOR UNIVERSAL COLORANT, at most 5%.

In general we recommend:

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply in full sun or high temperatures of the surface.
-) Perfectly mix the product before use.
-) In case of contamination by fungus or algae:
 - Wash with a solution of water and bleach to 10%.
 - Rinse with water.
 - Let dry completely before beginning to paint.
 - Use products with protection against FUNGUS.
-) In case of presence of saline efflorescence:
 - Brush and wash with hydrochloric acid diluted to 10% with water.
 - Rinse with water.
 - Let dry completely before beginning to paint.

PRESENTATION:

Metallic packaging of: 0.750 Litres; 4 Litres

STORAGE:

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14 Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

ANTI-HUMIDITY PAINT



ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14 Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>