



TECHNICAL INFORMATION

MATT PAINT BLACK



DESCRIPTION:

High quality matt paint for decoration and protection of interior and exterior surfaces.

Features:

-) High covering.
-) Weather and sunlight proof.
-) Excellent brushability and leveling.
-) Resistant to alkalis.
-) Good adherence.
-) Very low tendency to drip.
-) Totally washable after 15 days.

TECHNICAL DATA:

Fixed vehicle	Copolymer styrene acrylic.	
Colour	Black.	
Gloss	Matt G4. 85°: ≤ 5	UNE-EN 13300
Solids by weight	63 %	UNE-EN ISO 3251
Solids by volume	36 %	UNE 48090
Viscosity	98 – 104 KU (23 ± 2 °C)	UNE 48076
Specific weight	1.60 – 1.70 kg/l (23 ± 2 °C)	UNE-EN ISO 2811-1
pH	8.0 – 10.0 (23 ± 2 °C)	UNE-EN ISO 787-9
Theoretical spreading rate	8 – 12 m ² /l and coat. Take in mind application leaking, surface irregularities, etc.	
Recommended thickness	80 – 125 microns wet; 30 – 45 microns dry per coat. Apply 2 coats as finish.	
Total drying	30 – 60 minutes.	UNE 48301
Repaint	4 – 6 hours.	
Solvent	Water.	
Wet scrub resistance	Class 2	UNE-EN 13300
Reaction to fire	Class M-1	UNE 23727
Reaction to fire	Bs1d0	UNE-EN 13501-1:2007

EU limit value for this product (cat. A/a): 30 g/l (2010). Max. content VOC: 1 g/l

APPLICATION:

Protection and decoration of interior and exterior. Suitable walls and ceilings of brick, concrete, plaster, and brickwork in general.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

MATT PAINT BLACK



INSTRUCTIONS FOR USE:

Application methods: brush, roller or spray.

Thinner and cleaning utensils: Water.

Painted surfaces must be dry and clean of dust, rust, grease, etc. and primed properly.

) Unpainted surfaces:

- Gypsum, cement and lime: Apply a first coat diluted 10 – 15% with water or PENETRATING DECOKRIL. Apply two coats of MATT BLACK diluted to 10% with water for finish.
- Iron, steel: Prime with PRIMER ANTIRUST DECOLOR or PRIMER POLYVALENT AQUA. . Apply two coats of MATT BLACK diluted to 10% with water for finish.
- Wood: Prime with SEALER DECOLOR or SEALER AQUA. Apply two coats of MATT BLACK diluted to 10% with water for finish.
- "Dead" or powdery plaster: Prime with PENETRATING DECOKRIL. Apply two coats of MATT BLACK diluted to 10% with water for finish.

) Painted surfaces:

- If the paint is in poor condition, remove completely and proceed as in unpainted surfaces.
- If the paint is in good condition, wash and sand and apply MATT BLACK.
- If there is fungus or algae formations clean previously.

In general we recommend:

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply in full sun or high temperatures of the surface.
-) Perfectly mix the product before use.
-) In case of contamination by fungus or algae:
 - Wash with a solution of water and bleach to 10%.
 - Rinse with water.
 - Let dry completely before beginning to paint.
 - Use products with protection against FUNGUS.
-) In case of presence of saline efflorescence:
 - Brush and wash with hydrochloric acid diluted to 10% with water.
 - Rinse with water.
 - Let dry completely before beginning to paint.

PRESENTATION:

Plastic packaging of: 4 L; 14 L

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

MATT PAINT BLACK



STORAGE:

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>