



TECHNICAL INFORMATION

SMOOTH REVETMENT



DESCRIPTION:

Smooth revetment for the protection and decoration of façades.

Features:

-) Good covering and filling power.
-) Transpiring and waterproofing.
-) Excellent leveling and brushability.
-) Alkaline and weather resistant.
-) Stable pigment and light resistant.

TECHNICAL DATA:

Fixed vehicle	Copolymer styrene acrylic.	
Colour	White.	
Gloss	Matt. 60°: 2-3 GU	UNE-EN ISO 2813
Solids by weight	70 %	UNE-EN ISO 3251
Solids by volume	47 %	UNE 48090
Viscosity	115 – 121 KU (23 ± 2 °C)	UNE 48076
Specific weight	1.65 – 1.75 Kg./l (23 ± 2 °C)	UNE-EN ISO 2811-1
pH	8.0 – 10.0 (23 ± 2 °C)	UNE-EN ISO 787-9
Theoretical spreading rate	7 – 9 m ² /l and coat. Take in mind application leaking, surface irregularities, etc.	
Recommended thickness	110 – 140 microns wet; 52 – 66 microns dry per coat. Apply 2 coats as finish.	
Total drying	1 hour.	UNE 48301
Repaint	4 – 6 hours.	
Solvent	Water.	
Reaction to fire	Class M-1	UNE 23727
Reaction to fire	Bs1d0	UNE-EN 13501-1:2007
Wet scrub resistance	Class 2	UNE-EN 13300
Permeability to water vapour	Class II (Medium)	UNE-EN ISO 7783-2
Liquid water transmission rate	Class II (Medium)	UNE-EN 1062-3
Classification	EN 1062-1 G ₃ E ₂ S ₁ V ₂ W ₂ A ₀ C ₀	UNE-EN 1062-1

EU limit value for this product (cat. A/c): 40 g/l (2010). Max. content VOC: 8.5 g/l

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14 Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

SMOOTH REVETMENT



APPLICATION:

Smooth revetment for the protection and decoration of all types of surfaces of concrete, exterior brickworks, etc.

INSTRUCTIONS FOR USE:

Application methods: brush, roller or spray.

Thinner and cleaning utensils: Water.

Painted surfaces must be dry and clean of dust, rust, grease, etc. and primed properly.

) Unpainted surfaces:

- Gypsum, cement and lime: Prime with DECOKRIL or PENETRATING DECOKRIL. Apply SMOOTH REVETMENT as a finishing.
- Iron, steel: Prime with PRIMER ANTIRUST DECOLOR or PRIMER POLYVALENT or PRIMER POLYVALENT AQUA. Apply SMOOTH REVETMENT as a finishing.
- Wood: Prime with SEALER DECOLOR or SEALER AQUA. Apply SMOOTH REVETMENT as a finishing.
- "Dead" or powdery plaster: Prime with PENETRATING DECOKRIL. Apply SMOOTH REVETMENT as a finishing.

) Painted surfaces:

- If the paint is in poor condition, remove completely and proceed as in unpainted surfaces.
- If the paint is in good conditions, wash, sand and apply two coats of SMOOTH REVETMENT as a finishing. For a better consistence and durability of the coating we advise to prime first the surface using DECOKRIL PENETRANT.

If you want to colour it can be used DECOLOR WATER COLORANT or DECOLOR UNIVERSAL COLORANT, at most 5%.

In general we recommend:

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply in full sun or high temperatures of the surface.
-) Perfectly mix the product before use.
-) In case of contamination by fungus or algae:
 - Wash with a solution of water and bleach to 10%.
 - Rinse with water.
 - Let dry completely before beginning to paint.
 - Use products with protection against FUNGUS.
-) In case of presence of saline efflorescence:

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14 Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

SMOOTH REVETMENT



- Brush and wash with hydrochloric acid diluted to 10% with water.
- Rinse with water.
- Let dry completely before beginning to paint.

PRESENTATION:

Plastic packaging of: 4 Litres; 14 Litres

STORAGE:

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14 Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>