



TECHNICAL INFORMATION

ANTIGRAFFITI AQUA



DESCRIPTION:

Anti-adherent product, specially developed for the easy removal of graffiti and due to its non-stick nature, it prevents dirt and dust from adhering.

Characteristics:

-) Prevents penetration of aqueous products.
-) Prevents the penetration of oils, greases and inks that stain the treated surface.
-) Simple cleaning of graffiti.
-) Non-stick.
-) Excellent leveling and brushability.
-) Respectful with the environment.
-) Solvent free.
-) Odorless.

TECHNICAL DATA:

Appearance	Milky liquid	
Specific weight	0.90 – 1.00 Kg./l. (23 ± 2 °C)	UNE-EN ISO 2811-1
pH	8 – 10 (23 ± 2 °C)	UNE-EN ISO 787-9
Total drying	5 minutes	UNE 48301
Repaint	20 minutes	
Solvent	Water	

EU limit value for this product (cat. A/i): 140 g/l (2010). Max. content VOC: 0 g/l

APPLICATION:

It is applied as a surface treatment in walls, walls, etc. Of bricks, natural stones, concrete, tiles, etc. Facilitating the removal of graffiti, stickers and posters.

It can also be applied to facilitate the maintenance of natural stones and ceramic floors. Due to its water-repellent function, it can be used to protect mineral supports exposed to rain, window frames, stone slabs, etc.

INSTRUCTIONS FOR USE:

Application methods: brush, roller or spray.

Cleaning utensils: Water.

-) Preparation of the substrate.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14 Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

ANTIGRAFFITI AQUA



The surfaces to be treated must be dry and free of dust, rust, grease, etc. And be absorbent. On non-absorbent surfaces perform a test beforehand.

-) Preparation of the product.
Homogenize the product and then make a 1:1 dilution with water. Add water on the product for dilution and not vice versa.
-) Application and drying.
Apply two layers of the product with a drying time of 20 minutes between layers.
The surface is protected 60 minutes after application of the second layer.
-) Application and drying.
For the removal of graffiti, stains, etc. Apply a jet of water under pressure. Once the stains have been removed, wait for the surface to dry and apply ANTI-GRAFFITI AQUA as explained above.
-) Durability to the outside.
This coating is a sacrificial coating; it means it is not permanent. The primary purpose of such a coating is to protect the surfaces of the stains such as graffiti. The durability of the coating is affected by environmental influences such as rain, humidity, solar radiation, etc., therefore, the durability varies and cannot be specified.

In general we recommend:

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply in full sun or high temperatures of the surface.
-) Perfectly mix the product before use it.

PACKAGING:

Plastic packaging of: 0,750 Litres; 4 Litres

STORAGE:

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain
Phone: +34 967 44 17 14 Fax: +34 967 44 33 54
E-mail: dptotecnico@decolor.com <http://www.decolor.com>