



TECHNICAL INFORMATION

DECOFORJA ANTIOXYDANT



DESCRIPTION:

Synthetic enamel forge/wrought finish made from alkyds resins and antirust pigments obtaining a fine texture easy to clean.

Features:

-) High coverage.
-) Excellent leveling and brushability.
-) High hardness against scratches and hits.
-) Resistant to chemical products.
-) Weather resistant.
-) Antirust.

TECHNICAL DATA:

Fixed vehicle	Alkyd resins.	
Colour	According to DECOFORJA colour chart.	
Gloss	Forge/wrought finish.	
Solids by weight	77 %	UNE-EN ISO 3251
Solids by volume	57 %	UNE 48090
Viscosity	94 – 100 KU (23 ± 2 °C)	UNE 48076
Specific weight	1.60 – 1.70 Kg./l (23 ± 2 °C)	UNE-EN ISO 2811-1
Theoretical spreading rate	8 – 12 m ² /l and coat. Take in mind application leaking, surface irregularities, etc.	
Recommended thickness	80 – 125 microns wet; 45 – 70 microns dry per coat. Apply 2 coats as finish.	
Total drying	3 – 4 hours.	UNE 48301
Repaint	12 – 24 hours.	
Solvent	Aliphatic solvent.	
Reaction to fire	Class M-1	UNE 23727
Reaction to fire	Bs1d0	UNE-EN 13501-1:2007

EU limit value for this product (cat. A/i): 500 g/l (2010). Max. content VOC: 400 g/l

APLICACION:

Decoration and protection of surfaces of iron/steel against corrosion, for both interior and exterior where you want to obtain a metallic forge/wrought finish.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5
 Apdo. 106 – 02630 La Roda (Albacete) Spain
 Phone: +34 967 44 17 14 Fax: +34 967 44 33 54
 E-mail: dptotecnico@decolor.com <http://www.decolor.com>



TECHNICAL INFORMATION

DECOFORJA ANTIOXYDANT



INSTRUCTIONS FOR USE:

Application methods: brush or spray.

Thinner and cleaning utensils: SOLVENT SYNTHETIC AND FATTY.

Painted surfaces must be dry and clean of dust, rust, grease, etc. and primed properly.

) Unpainted surfaces:

- Iron, steel: Apply DECOFORJA ANTIOXYDANT for finish. Prime previously the surface using PRIMER ANTIOXYDANT DECOLOR or PRIMER POLYVALENT, if you need more anti rust protection.
- Gypsum, cement, wood: Prime with SEALER DECOLOR. Apply DECOFORJA ANTIOXYDANT for finish.
- Other metals (aluminium, galvanized, etc.): Prime previously the surface using PRIMER POLYVALENT. Apply DECOFORJA ANTIOXYDANT as a finish.

) Painted surfaces:

- If the paint is in poor condition, remove completely and proceed as in unpainted surfaces.
- If the paint is in good condition, sand and apply DECOFORJA ANTIOXYDANT.

In general we recommend:

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply in full sun or high temperatures of the surface.
-) Perfectly mix the product before use.

PRESENTATION:

Metal packaging of: 0.750 Litres; 4 Litres

STORAGE:

24 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14 Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>