



TECHNICAL INFORMATION

DECOKRIL



DESCRIPTION:

Concentrated water-based primer with a high fixation and penetration power into damaged substrates, improving adhesion and getting uniform its absorption.

Features:

-) Excellent adherence on porous supports.
-) High penetration on porous substrates.
-) Reinforce the substrates.
-) Makes uniform the absorption of the substrate.
-) Resistant to water and weather.
-) Alkali-resistant substrates.
-) Exterior and interior.
-) Anti-carbonation.
-) Eco friendly.
-) Solvents free.

TECHNICAL DATA:

Fixed vehicle	Acrylic copolymer.	
Colour	Colourless.	
Solids by weight	50 %	UNE-EN ISO 3251
Solids by volume	50 %	UNE 48090
Specific weight	1.00 – 1.10 Kg./l (23 + 2 °C)	UNE-EN ISO 2811-1
pH	> 8.0 (23 + 2 °C)	UNE-EN ISO 787-9
Theoretical spreading rate	25 – 30 m ² /l and coat. Take in mind application leaking, surface irregularities, etc.	
Reaction to fire	Bs1d0	UNE-EN 13501-1:2007
Total drying	30 – 60 minutes.	UNE 48301
Repaint	4 hours.	
Solvent	Water.	

EU limit value for this product (cat. A/h): 30 g/l (2010). Max. content VOC: 2 g/l

APLICACION:

Fixing of walls, ceilings and certain stands experiencing difficulty of adherence, indoor and outdoor, for old paintings or temple before being painted with plastic paint. Avoid different absorptions of the facing.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5

Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

DECOKRIL



INSTRUCTIONS FOR USE:

Application methods: brush or roller.
Thinner and cleaning utensils: Water.

Dilute 1 part of DECOKRIL with 3-4 parts water.

Painted surfaces must be dry and clean of dust, rust, grease, etc.

) Unpainted surfaces:

- Dead or powdery plaster, cement, brickwork: Fix the surface DECOKRIL. Once is dry apply the coat that you want as a finishing.

) Painted surfaces:

- If the paint is in poor condition, remove completely and proceed as in unpainted surfaces.
- If the paint is in good conditions wash, sand and fix the surface to be painted with DECOKRIL. Once is dry applying the coat that you want as a finishing.

In general we recommend:

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply in full sun or high temperatures of the surface.
-) Perfectly mix the product before use.
-) In case of contamination by fungus or algae:
 - Wash with a solution of water and bleach to 10%.
 - Rinse with water.
 - Let dry completely before beginning to paint.
 - Use products with protection against FUNGUS.
-) In case of presence of saline efflorescence:
 - Brush and wash with hydrochloric acid diluted to 10% with water.
 - Rinse with water.
 - Let dry completely before beginning to paint.

PRESENTATION:

Plastic packaging of: 0.750 Litres; 5 Litres; 10 Litres

STORAGE:

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain
Phone: +34 967 44 17 14 Fax: +34 967 44 33 54
E-mail: dptotecnico@decolor.com <http://www.decolor.com>



TECHNICAL INFORMATION

DECOKRIL



ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14 Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com <http://www.decolor.com>