



TECHNICAL INFORMATION

PRIMER PROTECTION AQUA



DESCRIPTION:

Protective impregnating primer of high-quality wood from acrylic resins for the protection of the wood in depth.

Features:

-) Prevents the absorption of water, humidity and regulates transpiration of the wood, eliminating deformation and cracks.
-) Highlight the natural appearing of the wood.
-) No peeling off.
-) Micro porous film.
-) Breathable to water vapour (inside the wood).
-) Fast drying.
-) Interior and exterior.

TECHNICAL DATA:

Fixed vehicle	Acrylics resins.	
Colour	Chart colours BARNIZ – LASUR.	
Gloss	Satin	
Solids by weight	16 %	UNE-EN ISO 3251
Solids by volume	15 %	UNE 48090
Specific weight	0.95 – 1.05 Kg./l (23 ± 2 °C)	UNE-EN ISO 2811-1
pH	>8.0 (23 ± 2 °C)	UNE-EN ISO 787-9
Theoretical spreading rate	10 – 12 m ² /l. Take in mind application leaking, surface irregularities, etc.	
Total drying	30 – 60 minutes.	UNE 48301
Repaint	4 – 6 hours.	
Solvent	Water.	

EU limit value for this product (cat. A/e): 130 g/l (2010). Max. content VOC: 10 g/l

APPLICATION:

Impregnation treatment of wood to protect outdoors. Penetrating into the wood and prevents the absorption of water, humidity and regulates transpiration of the wood, eliminating deformation and cracks.

INSTRUCTIONS FOR USE:

Application methods: brush or spray.
Thinner and cleaning utensils: Water.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain
Phone: +34 967 44 17 14 Fax: +34 967 44 33 54
E-mail: dptotecnico@decolor.com <http://www.decolor.com>



TECHNICAL INFORMATION

PRIMER PROTECTION AQUA



Painted surfaces must be dry and clean of dust, rust, grease, etc.

The number of coats to apply of tinted PRIMER PROTECTION AQUA will affect the obtained final colour.

The wood highly resinous must be cleaned previously with SYNTETIC AND GREASE SOLVENT, UNIVERSAL SOLVENT or ODOURLESS SOLVENT, to avoid problems during the drying.

) Unpainted surfaces:

- Wood in general: Apply 1-2-3 coats of PRIMER PROTECTION AQUA with an interval between them of 4 – 6 hours and sanding smoothly between coats.

) Painted surfaces:

- Remove paint and varnish by polishing or sanding until complete elimination. After that proceed as non painted surfaces

In general, we recommend:

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply in full sun or high temperatures of the surface.
-) Perfectly mix the product before use.

PRESENTATION:

Plastic packaging of: 0.750 Litres; 4 Litres

STORAGE:

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14 Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>