



TECHNICAL INFORMATION

ANTIOXYDANT PRIMER



DESCRIPTION:

Primer formulated from alkyds resins specially indicated for maintenance works.

Features:

-) Excellent adherence over metallic surfaces.
-) Rust and exterior resistant.
-) Excellent leveling and brushability.
-) Fast drying.
-) High covering power.

TECHNICAL DATA:

Fixed vehicle	Alkyds resins.	
Colour	White, Blue, Red, Grey, Green, Black and Orange.	
Gloss	Matt.	UNE-EN ISO 2813
Solids by weight	71 %	UNE-EN ISO 3251
Solids by volume	51 %	UNE 48090
Viscosity	88 – 96 KU (23 ± 2 °C)	UNE 48076
Specific weight	1.45 – 1.55 Kg./l (23 ± 2 °C)	UNE-EN ISO 2811-1
Theoretical spreading rate	10 – 14 m ² /l and coat. Take in mind application leaking, surface irregularities, etc.	
Recommended thickness	70 – 100 microns wet; 40 – 56 microns dry per coat. Apply 2 coats as finish.	
Total drying	30 – 60 minutes.	UNE 48301
Repaint	12 – 24 hours.	
Solvent	Aromatic solvent.	
Corrosion test (salt mist)	> 240 hours of exposure (ratio value 7; dry thickness 45 µm)	ASTM B-117

EU limit value for this product (cat. A/i): 500 g/l (2010). Max. content VOC: 415 g/l

Adhesion / Lattice cut test UNE-EN ISO 2409		
Surface	Details	Resulted
Carbon steel	50 µm dry applied directly; 7 days at room temperature	0/0/0

APPLICATION:

Undercoating of metallic surfaces of iron or steel for interior and exterior where you want to obtain a good antirust protection.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3^a, Parcels 4 and 5
 Apdo. 106 – 02630 La Roda (Albacete) Spain
 Phone: +34 967 44 17 14 Fax: +34 967 44 33 54
 E-mail: dptotecnico@decolor.com <http://www.decolor.com>



TECHNICAL INFORMATION

ANTIOXYDANT PRIMER



INSTRUCTIONS FOR USE:

Application methods: brush, roller or spray.

Thinner and cleaning utensils: SOLVENT UNIVERSAL.

Painted surfaces must be dry and clean of dust, rust, grease, etc.

) Unpainted surfaces:

- Iron or Steel: The surface to be painted should be dry and clean of dust, oxide, grease, etc. Clean previously manually or mechanically the surface to be painted. Apply after a first coat of ANTIOXYDANT PRIMER diluted 5%, further coats non diluted or diluted a maximum of 5%.

) Painted surfaces:

- If the paint is in poor condition, remove completely and proceed as in unpainted surfaces.
- If the paint is in good conditions, brush the rust areas and clean with water, let dry and apply ANTIOXYDANT PRIMER.

If you want to colour it can be used DECOLOR UNIVERSAL COLORANT, at most 5%.

In general, we recommend:

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply in full sun or high temperatures of the surface.
-) Perfectly mix the product before use.

PRESENTATION:

Metal packaging of: 0.750 Litres; 4 Litres; 15 Litres

STORAGE:

24 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14 Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>