



TECHNICAL INFORMATION

D-300 MATT PAINT



DESCRIPTION:

Matt paint for the decoration and protection of both interior and exterior walls. Paint with a coating protect that provides an excellent protection against a wide range of fungus and algae.

Features:

-) High opacity and whiteness.
-) Excellent levelling and brushability.
-) Good adhesion.
-) Breathable.
-) Tendency to leak very small.

TECHNICAL DATA:

Fixed vehicle	Copolymer styrene acrylic.	
Colour	White.	
Gloss	Matt G3. 85°: $5 < X < 10$	UNE-EN ISO 2813
Solids by weight	70 %	UNE-EN ISO 3251
Solids by volume	47 %	UNE 48090
Viscosity	110 – 115 KU (23 ± 2 °C)	UNE 48076
Specific weight	1.60 – 1.70 Kg./l (23 ± 2 °C)	UNE-EN ISO 2811-1
pH	8.5 – 10.0 (23 ± 2 °C)	UNE-EN ISO 787-9
Theoretical spreading rate	7 m ² /l. Take in mind application leaking, surface irregularities, etc.	
Opacity	Class 2	UNE-EN 13300
Theoretical spreading rate	5 m ² /l. Take in mind application leaking, surface irregularities, etc.	
Opacity	Class 1	UNE-EN 13300
Total drying	30 – 60 minutes.	UNE 48301
Repaint	4 – 6 hours.	
Solvent	Water.	
Wet scrub resistance	Class 2	UNE-EN 13300
Reaction to fire	Class M-1	UNE 23727
Reaction to fire	Bs1d0	UNE-EN 13501-1:2007
Emissions in the indoor air	Class A+	French Legislation Decree No. 2011-321 of March 23, 2011

EU limit value for this product (cat. A/a): 30 g/l (2010). Max. content VOC: 15 g/l

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5

Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14

Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

D-300 MATT PAINT



APPLICATION:

Protection and decoration of plaster, cement and masonry in general, in walls, ceilings, etc. both indoor and outdoor.

INSTRUCTIONS FOR USE:

Application methods: brush, roller or spray gun.

Thinner and cleaning utensils: Water.

Painted surfaces must be dry and clean of dust, rust, grease, etc. and primed properly.

) Unpainted surfaces:

- Gypsum, cement and lime: Apply a first layer of diluted to 10-15% with water or PENETRATING DECOKRIL. Then, apply two coats diluted with water between 5-10%.
- Iron, steel: primed with PRIMER POLIVALENT AQUA or PRIMER ANTIRUST DECOLOR. Apply two layers of MATT D-300 ANTI-FUNGUS like finish between 5-10% diluted with water.
- Wood: Primed with SEALER DECOLOR. Apply two layers of MATT D-300 ANTI-FUNGUS like finish between 5-10% diluted with water.
- "Dead" or powdery plaster: fix with PENETRATING DECOKRIL. Apply two layers of MATT D-300 ANTI-FUNGUS like finish between 5-10% diluted with water.

) Painted surfaces:

- If the painting is in poor condition, remove it completely and proceed as on unpainted surfaces.
- If the paint is in good condition, wash and sand and apply MATT D-300 ANTI-FUNGUS.

If you want to colour it can be used DECOLOR WATER COLORANT or DECOLOR UNIVERSAL COLORANT, at most 5%.

In general we recommend:

-) Apply between 5 °C and 35 °C.
-) It is not recommended to apply in full sun or high temperatures of the surface.
-) Perfectly mix the product before use.
-) In case of contamination by fungus or algae:
 - Wash with a solution of water and bleach to 10%.
 - Rinse with water.
 - Let dry completely before beginning to paint.
 - Use products with protection against FUNGUS.
-) In case of presence of saline efflorescence:
 - Brush and wash with hydrochloric acid diluted to 10% with water.
 - Rinse with water.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14 Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>



TECHNICAL INFORMATION

D-300 MATT PAINT



- Let dry completely before beginning to paint.

PRESENTATION:

Plastic packaging of: 0,750 L; 4 L; 14 L

STORAGE:

12 months in closed original container under roof and temperatures between 5 °C and 35 °C and protected from the weather.

ADDITIONAL INFORMATION:

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Data Sheet.

Pinturas Decolor

Industrial Estate El Salvador Avenue 3ª, Parcels 4 and 5
Apdo. 106 – 02630 La Roda (Albacete) Spain

Phone: +34 967 44 17 14 Fax: +34 967 44 33 54

E-mail: dptotecnico@decolor.com

<http://www.decolor.com>